



Quality Products Since 1932 • DRYLOK® • ZAR® • UGL®

## Graco® Spray Specifications DRYLOK® Extreme Waterproofer

### 1 to 15 gallons

Use Graco® Magnum Pro X21 (Part # 17G182) or larger Graco® sprayer. Remove gun and manifold filters prior to spraying. Use Graco® .019 RAC True Airless tip (TRU-419 8" fan pattern or TRU-519 10" fan pattern). Spray pressure 2200 - 2500 psi. Hold gun 12" from surface when spraying. Spray cross hatching patterns (north/south then east/west) with two coats, building to a 14 - 16 wet mil thickness. Back brush (DRYLOK® Brush) the first coat to fill all pores and pinholes. Give first coat 3 hours to dry, and then apply a second coat. Back brush as above or back roll second coat using ¾" nap cover, working DRYLOK® Extreme into the pores of the masonry and making sure to fill all pores and pinholes.

### 17 to 30 gallons

Use Graco® 210es (Part # 261-830) / Graco® 390 (Part # 17C310) or larger Graco® sprayer. Remove gun and manifold filters prior to spraying. Use Graco .019 True Airless tip (TRU-419 8" fan pattern or TRU-519 10" fan pattern). Spray pressure 2200 - 2500 psi. Spray cross hatching patterns (north/south then east/west) with two coats, building to a 14 - 16 wet mil thickness. Back brush (DRYLOK® Brush) the first coat to fill all pores and pinholes. Give first coat 3 hours to dry, and then apply a second coat. Back brush as above or back roll second coat using ¾" nap cover, working DRYLOK® Extreme into the pores of the masonry and making sure to fill all pores and pinholes.

### 31+ gallons

Use Graco® Ultra Max II 490 (Part #17C327) or larger Graco® sprayer. Remove gun and manifold filters prior to spraying. Use Graco® .021 True Airless tip (TRU-421 8" fan pattern or TRU-521 10" fan pattern). Spray pressure 2200 - 2500 psi. Spray cross hatching patterns (north/south then east/west) with two coats, building to a 14 to 16 wet mil thickness. Back brush (DRYLOK® Brush) the first coat to fill all pores and pinholes. Give first coat 3 hours to dry, and then apply a second coat. Back brush as above or back roll second coat using ¾" nap cover, working DRYLOK® Extreme into the pores of the masonry and making sure to fill all pores and pinholes.

Revised February 21, 2019

570-344-1202 • 1-800-845-5227 • Fax 570-969-7634 • [www.UGL.com](http://www.UGL.com)

Corporate Office: 1396 Jefferson Avenue, Dunmore, PA 18509 • Mail to: P.O. Box 70, Scranton, PA 18501-0070  
Plant Locations: Jacksonville, IL • Jackson, MS