



### COVERAGE

200–400 square feet per gallon



### COAT

Recommended



### DRY TIME

1 Hour



### CLEAN-UP

Soap and water

Dispose of contaminated absorbent, container, and unused contents in accordance with local, state, and federal regulations.

# PRODUCT DATA SHEET

Publication Date: 9–15–20

## DRYLOK® WetLook Clear High Gloss Penetrating Sealer

### PRODUCT DESCRIPTION

DRYLOK® Wetlook Clear High Gloss Penetrating Sealer is a clear, nonyellowing, water-based acrylic coating formulated for use on interior or exterior masonry surfaces. Provides superior hardness and durability. Protects against efflorescence (white, powdery, salt-like deposits) visible on the masonry. Built in flash rust resistance prevents orange staining of surface when applied to masonry containing natural metals. Excellent chemical resistance to de-icing salts. Compatible with polymeric sand.

- Our highest level of moisture vapor barrier protection (25% solids)
- Resists de-icing salts
- Interior/exterior
- Use on bare masonry or previously painted surfaces
- SaltLok® Technology helps prevent the leaching of minerals and salt

### BASIC USES

Ideal for horizontal and vertical masonry surfaces such as walkways, concrete driveways, garage floors, basement floors, concrete sidewalks, pavers, bare or painted brick, poured concrete, Chattahoochee stone, stamped concrete and artificial stone, terrazzo, and slate surfaces.

### TECHNICAL DATA

**COMPOSITION:** Latex Base

**SHEEN:** High Gloss

**% WEIGHT SOLIDS:** 25% ± 0.5%

**DENSITY (LBS./US GAL.):** 8.5 ± 0.3

**VISCOSITY:** 12-18 Seconds #4 Ford Cup @ 77°F

**pH:** 8.5-9.5

**COLORS:**

- Transparent

## DRYLOK® WETLOOK CLEAR HIGH GLOSS PENETRATING SEALER

### DRY TIME:

- To touch: 1 hour
- To recoat: 4 hours
- Light foot traffic: 24 hours
- Heavy foot traffic: 72-96 hours
- Clean with a mild, non-abrasive liquid detergent: 30 days
- Rain free: 24 hours

Note: Maximum cure and dry time will be prolonged when slightly humid and damp, cool conditions prevail.

### COVERAGE:

- 200-400 sq. ft./gal.

Note: Actual coverage will vary depending upon application method, surface texture, and porosity.

### RECOMMENDED FILM THICKNESS/COAT:

4 wet mils/coat (100 microns)

**SHELF LIFE:** 5 years unopened container

**Freeze/Thaw:** Keep from freezing

**CONTAINER SIZES:** 1 gallon and 5 gallon containers

### VOC

Does not exceed 100 g/L

### TINTING

N/A

### LIMITATIONS

DRYLOK® WetLook Clear High Gloss Penetrating Sealer is not for use on wood, metal, granite, marble, over silicone treated surfaces, or on any masonry surface subjected to hydrostatic pressure. Vertical masonry surfaces subjected to hydrostatic pressure should be treated with DRYLOK® Masonry Waterproofer.

### SURFACE PREPARATION

Remove all dirt, wax, dust, mildew, and loose or scaling material with a scraper, wire brush, or stiff bristle brush. Masonry surface must be dry and free of dirt, wax, dust, mildew, and loose or scaling material. For proper penetration and adhesion to extremely smooth

bare concrete floors, use DRYLOK® ETCH (liquid or powder) or muriatic acid. Rinse thoroughly (pressure wash for best results). Allow to dry thoroughly according to manufacturer's directions.

If using a pressure washer, do not use on a pressure setting above 1750 PSI to avoid damaging the concrete. Remember, concrete acts like a stone sponge. Pressure washing and general cleaning may trap residual moisture in the concrete.

To check for trapped moisture, tape a 12"x12" piece of 3 mil plastic or aluminum foil tightly on all four edges to the surface. Remove it after 24 hours. If the floor side of the plastic or foil is damp, allow additional drying and repeat the test.

**EFFLORESCENCE** a white, powdery, crystal-like deposit visible on the masonry surface must be removed. DRYLOK® Etch (liquid or powder) or muriatic acid, used according to manufacturer's directions, are effective efflorescence removal agents. All masonry surfaces are subject to occurrences of efflorescence. Properly prepared concrete should look and feel like medium grit sandpaper. If concrete remains smooth, repeat etching procedure.

Test concrete porosity by sprinkling a few drops of water onto the surface in several areas. If the water is readily absorbed, you are ready to paint. If it beads or lays on the surface additional cleaning and etching is needed. Rinse thoroughly with clean water and allow to dry for 24 hours.

**NOTE:** Rinse etching solutions thoroughly. Etching solution allowed to dry on the masonry surface will prevent proper penetration and curing of the DRYLOK® Wetlook Clear High Gloss Penetrating Sealer. Surface must be thoroughly dry. Do not apply to damp surfaces. For exterior surfaces, do not apply if rain is expected within 48 hours. Wait for a dry, rain-free period

New concrete and freshly applied Portland cement based patching compounds must be cured for a minimum of 24 hours prior to application of DRYLOK® Wetlook Clear High Gloss Penetrating Sealer.

## DRYLOK® WETLOOK CLEAR HIGH GLOSS PENETRATING SEALER

Patch all holes and cracks with a suitable cement based patching compound. Be sure to smooth the patch evenly. Allow the patched area to dry thoroughly.

**Previously painted masonry surfaces:** In addition to normal surface preparation old glossy surface must have the gloss removed by using sandpaper. Remove all sanding dust with a vacuum or tack cloth.

### APPLICATION

Stir thoroughly. Use only when air and surface temperatures are between 50°-95°F (10°-35°C). Surface must be thoroughly dry. Do not apply in direct sunlight. Do not apply to wet surfaces or if rain or heavy dew is expected within 24 hours before or after application. Apply a thin coat using a 3/8"1/2" nap roller or use a nylon/polyester brush at a spread rate of 1000-2000 sq. ft. per 5 gallon. Spread rate is highly dependent on surface porosity, 1-2 coats are all that is required to achieve a high gloss appearance.

On exposed aggregate and on materials where product may puddle or pool, **over application** will extend drying times and surface may appear milky until fully dry.

**IMPORTANT:** Sealed surfaces and areas adjacent to pools may become slippery when wet. Use caution when walking on surface when moisture is present.

**OPTIONAL:** Up to 2 oz. of DRYLOK® NonSkid Texture Additive may be added to DRYLOK® Wetlook Clear High Gloss Penetrating Sealer to improve traction.

**For previously painted masonry surfaces** DRYLOK® Wetlook Clear High Gloss Penetrating Sealer may be applied over existing paints and coatings. Many previously coated surfaces may only require one coat. Test DRYLOK® Wetlook Clear High Gloss Penetrating Sealer on a small area to determine compatibility prior to completing the entire job

### THINNING

Due to variations in porosity, when applied over flagstone, slate, terrazo, dense smooth or light colored concrete, thin with equal parts of clean, luke warm water to minimize sheen variations as subsequent top coats are applied. Test on a small area to see final effect.

### SPECIFICATIONS

N/A

### MAINTENANCE

Horizontal surfaces subject to excessive wear may require periodic touch-ups to high traffic areas.

### CAUTION

**KEEP OUT OF REACH OF CHILDREN.  
DO NOT TAKE INTERNALLY .  
CLOSE CONTAINER AFTER EACH USE.  
KEEP FROM FREEZING  
USE WITH ADEQUATE VENTILATION.**

### FIRST AID

**EYES:** Flush immediately with large amounts of water for at least 15 minutes. Consult a physician if irritation persists.

**SKIN:** Wash affected areas with soap and water. Consult a physician if irritation persists.

**INGESTION:** Seek medical attention. If individual is drowsy or unconscious, do not give anything by mouth. Place individual on the left side with head down. Contact a physician, medical facility or poison control center for advice about whether to induce vomiting.

**INHALATION:** Remove to fresh air.

### WARNING

If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

## DRYLOK® WETLOOK CLEAR HIGH GLOSS PENETRATING SEALER

⚠Warning: Cancer and Reproductive Harm  
[www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov).

For additional health and safety information, please refer to the Safety Data Sheet (SDS).

DRYLOK® is a registered trademark of United Gilsonite Laboratories (UGL).

DISCLAIMER: This information is furnished without warranty, representation, inducement or license of any kind, except that it is accurate to the best of UGL's knowledge, or obtained from sources believed by UGL to be accurate, and UGL does not assume any legal responsibility for use or reliance upon same. Before using any product, read the label.

	CONTAINER	NUMBER/CASE	ORDER NUMBER
DRYLOK® WetLook Clear High Gloss Penetrating Sealer	1 gallon	2/case	28913
DRYLOK® WetLook Clear High Gloss Penetrating Sealer	5 gallon	1/case	28915



1-800-845-5227 • Fax 1-570-969-7634 • [www.UGL.com](http://www.UGL.com)

Corporate Office: 1396 Jefferson Avenue, Dunmore, PA 18509

Mail to: P.O. Box 70, Scranton, PA 18501-0070

Plant Locations: Jacksonville, IL • Jackson, MS