



# PRODUCT DATA SHEET

Publication Date: 7-31-2024

## DRYLOK® Natural Look Curing Membrane & Penetrating Sealer

### PRODUCT DESCRIPTION

- Water base, non-yellowing, one-coat penetrating sealer
- Ideal masonry primer
- Hardens concrete

### TECHNICAL DATA

**COMPOSITION:** Water base

**SHEEN:** Matte

**% WEIGHT SOLIDS:** 15% ± 0.5%

**% VOLUME SOLIDS:** 14% ± 0.5%

**DENSITY (LBS./US GAL.):** 8.4 ± 0.3

**VISCOSITY:** 11 seconds Ford #4 cup @ 75°F

**pH:** 8.1-8.5

**COLOR:**

- N/A

**DRY TIME:**

- Light foot traffic: 2 hours
- Heavy traffic: 24 hours
- To recoat: 3 hours

**Note:** Maximum cure and dry time will be prolonged when slightly humid and damp, cool conditions prevail.

**COVERAGE:**

- 400 sq. ft./gal.

**Note:** Actual coverage will vary depending upon application method, surface texture, and porosity.

**SHELF LIFE:** 5 years unopened container

**CONTAINER SIZES:** 1 gallon and 5 gallon containers



#### COVERAGE

400 square feet  
per gallon



#### COATS

Recommended



#### DRY TIME

2 Hours  
Recoat: 3 Hours



#### CLEAN-UP

Soap and water

Dispose of contaminated absorbent, container, and unused contents in accordance with local, state, and federal regulations.

### VOC

Does not exceed 100 g/L

### TINTING

N/A

### LIMITATIONS

DRYLOK® Natural Look is not recommended as a waterproofer. For masonry walls subjected to hydrostatic pressure, use DRYLOK® Masonry Waterproofer. Do not use over silicone treated surfaces. Do not apply on asphalt surfaces. Do not use as a primer/sealer in a garage setting when subject to vehicle traffic.

### SURFACE PREPARATION

**For freshly poured concrete:** Apply after concrete sets for at least 24 hours. Make sure no water puddles are present. Concrete may be slightly wet before applying.

**For fully cured concrete:** Remove all dirt, wax, dust, mildew, and loose or scaling material with a scraper, wire brush, or stiff bristle brush. Grease, wax, and oil should be removed by scrubbing with DRYLOK® Concrete and Masonry Etch and Cleaner or a heavy duty detergent in warm water. Rinse thoroughly with clean water. Allow to dry. If using a pressure washer, do not use on a pressure setting above 1750 psi to avoid damaging the concrete. Remember, concrete acts like a sponge - pressure washing and general cleaning may trap residual moisture in the concrete. To check for trapped moisture, tape a 12"x12" piece of 3 mil plastic or aluminum foil tightly on all four edges to the surface. Remove it after 24 hours. If the floor side of the plastic or foil is damp, allow additional drying and repeat the test.

**EFFLORESCENCE,** a white, powdery, crystal-like deposit visible on the masonry surface, should be removed. DRYLOK® ETCH or muriatic acid, used according to manufacturer's directions, are effective efflorescence removal agents. All masonry surfaces are subject to occurrences of efflorescence. Properly prepared concrete

should look and feel like medium grit sandpaper. If concrete remains smooth, repeat etching procedure. Test concrete porosity by sprinkling a few drops of water on to the surface in several areas. If the water is readily absorbed, you are ready to paint. If it beads or lays on the surface, additional cleaning and etching is needed. Rinse thoroughly with clean water and allow to dry for 24 hours.

**NOTE:** Rinse etching solutions thoroughly. Etching solutions allowed to dry on masonry surfaces prevent proper curing of the DRYLOK® finish coat and may result in the DRYLOK® Natural Look appearing milky when dry. Patch all holes and cracks with DRYLOK® Masonry Crack Filler, DRYLOK® Pourable Masonry Crack Filler, or a suitable cement-based patching compound. Be sure to smooth the patch evenly. Allow the patched area to dry thoroughly.

### APPLICATION

Apply only when air and surface temperature is above 50°F and humidity below 70%. Do not apply if raining or if it will rain within 48 hours of application. DRYLOK® Natural Look appears milky in the can but dries clear. Apply by brush, roller, spray, or squeegee. Spread evenly - do not allow puddles or a heavy surface film to occur. Apply one coat using thin even strokes. Extremely porous surfaces may require a second coat. Allow 6 hours drying time between coats. Additional coats will cause surface to be slippery when wet. On light-colored surfaces, some darkening may take place; test in an inconspicuous area to be sure darkening does not occur. May be applied to surfaces previously coated with a similar treatment. For best results, test a small area for proper adhesion prior to coating entire surface.

### THINNING

Due to variations in porosity, when applied over flagstone, slate, terrazo, dense smooth or light colored concrete, thin with clean, moderately warm water 10%—20% to minimize sheen

## DRYLOK® NATURAL LOOK

variations as subsequent top coats are applied. In addition, light colored concrete may darken unevenly due to variations in porosity. Test on a small area to see final effect.

### SPECIFICATION

DRYLOK® Natural Look meets A.S.T.M. Specification C-309.

### CAUTION

Avoid prolonged contact with skin or breathing of spray mist.

**KEEP OUT OF REACH OF CHILDREN.**

**DO NOT TAKE INTERNALLY.**

**KEEP FROM FREEZING**

### FIRST AID

**EYES:** Flush immediately with large amounts of water for at least 15 minutes. Consult a physician if irritation persists.

**SKIN:** Wash affected areas with soap and water. Consult a physician if irritation persists.

**INGESTION:** Seek medical attention. If individual is drowsy or unconscious, do not give anything by mouth. Place individual on the left side with head down. Contact a physician, medical facility or poison control center for advice about whether to induce vomiting.

**INHALATION:** Remove to fresh air.

### WARNING

If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

 **WARNING: Cancer and Reproductive Harm**  
- [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov).

For additional health and safety information, please refer to the Safety Data Sheet (SDS).

DRYLOK® is a registered trademark of United Gilsonite Laboratories (UGL).

DISCLAIMER: This information is furnished without warranty, representation, inducement or license of any kind, except that it is accurate to the best of UGL's knowledge, or obtained from sources believed by UGL to be accurate, and UGL does not assume any legal responsibility for use or reliance upon same. Before using any product, read the label.

|   | CONTAINER | NUMBER/CASE | ORDER NUMBER |
|---|-----------|-------------|--------------|
| DRYLOK® Natural Look Curing Membrane and Penetrating Sealer | 1 gallon  | 2/case      | 22113        |
| DRYLOK® Natural Look Curing Membrane and Penetrating Sealer | 5 gallon  | 1/case      | 22115        |



A SIKA COMPANY

1-800-845-5227 • Fax 1-570-969-7634 • [www.DRYLOK.com](http://www.DRYLOK.com)

Corporate Office: 1396 Jefferson Avenue, Dunmore, PA 18509  
Mail to: P.O. Box 70, Scranton, PA 18501-0070  
Plant Locations: Jacksonville, IL • Jackson, MS