

PRODUCT DATA SHEET

DRYLOK® Wet Look

Clear High Gloss Penetrating Sealer

DESCRIPTION

DRYLOK® Wet Look is a clear, nonyellowing, water-based acrylic coating for use on interior & exterior masonry surfaces. WetLook provides superior hardness and durability, while protecting against efflorescence (white, powdery, salt-like deposits) visible on the masonry. Built in flash rust resistance prevents orange staining of surface when applied to masonry containing natural metals.

USES

Ideal for horizontal/vertical masonry surfaces such as:

- Concrete walkways / driveway / sidewalks
- Basement / garage floors
- Bare/painted brick / slate / pavers / terrazzo
- Poured / Stamped concrete
- Chattahoochee / artificial stone

CHARACTERISTICS / ADVANTAGES

- Our highest level of moisture vapor barrier protection (25% solids)
- Resists de-icing salts
- Interior/exterior
- Use on bare masonry or previously painted surfaces
- SaltLok® Technology helps prevent the leaching of minerals and salt
- Compatible with polymeric sand

PRODUCT DATA SHEET

DRYLOK® Wet Look

May 2026, Version 01.02

021820301000000023

PRODUCT INFORMATION

Packaging	Size	PC/Case	Color	Order No.	Old Order No.
	5 gal	1	Clear	832425	28915
	1 gal	2	Clear	832423	28913
Shelf life	2 years in unopened container				
Storage conditions	Store between 50° F (10°C) and 85°F (29°C). Extreme heat or freezing temperatures can damage the product, causing it to separate or thicken. Avoid freezing. Keep away from direct sunlight.				
Density	8.5 ± 0.3 (LBS./US GAL.)				
Wet Film Thickness	4 wet mils per coat				
pH-Value	8.5-9.5				
Viscosity	12-18 Seconds #4 Ford Cup @ 77°F				
Solid content by mass	25% ± 0.5%				
Appearance	Clear - High Gloss				

APPLICATION INFORMATION

Number of Coats	1 - 2 (recommended)
Coverage	200 - 400 ft ² /gal Note: Actual coverage will vary depending upon application method, surface texture, and porosity.
Ambient air temperature	50°-95°F (10°-35°C)
Substrate temperature	50°-95°F (10°-35°C)
Drying time	<ul style="list-style-type: none">▪ To touch: 1 hour▪ To recoat: 2 hours▪ Light foot traffic: 24 hours▪ Heavy foot traffic: 72–96 hours Note: Maximum cure and dry time will be prolonged when slightly humid and damp, cool conditions prevail.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

- Not for use on wood, metal, granite, marble, over silicone treated surfaces.
- Not for use on any masonry surface subjected to hydrostatic pressure. Vertical masonry surfaces subjected to hydrostatic pressure should be treated with DRYLOK® Masonry Waterproofer.
- Allow 30 days of drying time before using a mild, non-abrasive liquid detergent to clean the surface of DRYLOK® Wet Look
- The product may turn hazy if over-applied (refer to coverage instructions) or if moisture becomes trapped within the substrate. Substrate moisture content must be below 10% before application.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

The surface should be clean, dry, and free from dirt, mildew, and loose or scaling material with a scraper,

wire brush, or stiff bristle brush. Masonry surface must be dry and free of dirt, wax, dust, mildew, and loose or scaling material. For proper penetration and adhesion to extremely smooth bare concrete floors, use muriatic acid or an etch solution. Rinse thoroughly (pressure wash for best results). Allow to dry thoroughly according to the manufacturer's directions. If using a pressure washer, do not use it on a pressure setting above 1750 PSI to avoid damaging the concrete. Remember, concrete acts like a stone sponge. Pressure washing and general cleaning may trap residual moisture in the concrete.

To check for trapped moisture, tape a 12"x12" piece of 3 mil plastic or aluminum foil tightly on all four edges to the surface. Remove it after 24 hours. If the floor side of the plastic or foil is damp, allow additional drying and repeat the test.

EFFLORESCENCE, a white, powdery, crystal-like deposit visible on the masonry surface, must be removed. Muriatic acid or an acid etch solution, used according to the manufacturer's directions, is an effective efflorescence removal agent. All masonry surfaces are subject to occurrences of efflorescence.

Test concrete porosity by sprinkling a few drops of water onto the surface in several areas. If the water is readily absorbed, you are ready to paint. If it beads or lies on the surface, additional cleaning and etching is needed. Rinse thoroughly with clean water and allow to dry for 24 hours.

New concrete and freshly applied portland cement-based patching compounds must be cured for a minimum of 24 hours prior to application of DRYLOK® Wet Look.

Patch all holes and cracks with a suitable cement based patching compound. Be sure to smooth the patch evenly. Allow the patched area to dry thoroughly.

Previously painted masonry surfaces: In addition to normal surface preparation old glossy surface must have the gloss removed by using sandpaper. Remove all sanding dust with a vacuum or tack cloth.

PRODUCT DATA SHEET

DRYLOK® Wet Look

May 2026, Version 01.02

021820301000000023

DRYLOK®

BUILDING TRUST



MIXING

Thinning

Due to variations in porosity, when applied over flagstone, slate, terrazo, dense smooth or light colored concrete, thin with clean, moderately warm water 10%—20% to minimize sheen variations as subsequent top coats are applied. Test on a small area to see final effect.

APPLICATION

Stir thoroughly. Use only when air and surface temperatures are between 50°-95°F (10°-35°C). Surface must be thoroughly dry. Do not apply in direct sunlight. Do not apply to wet surfaces or if rain or heavy dew is expected within 24 hours before or after application. Apply a thin coat using a 3/8"1/2" nap roller or use a nylon/ polyester brush at a spread rate of 1000-2000 sq. ft. per 5 gallon. Spread rate is highly dependent on surface porosity, 1-2 coats are all that is required to achieve a high gloss appearance.

On exposed aggregate and on materials where product may puddle or pool, over application will extend drying times and surface may appear milky until fully dry.

IMPORTANT: Sealed surfaces and areas adjacent to pools may become slippery when wet. Use caution when walking on surface when moisture is present.

OPTIONAL: Up to 2 oz. of DRYLOK® NonSkid Texture Additive may be added to DRYLOK® Wet Look to improve traction.

For previously painted masonry surfaces:

DRYLOK® Wet Look may be applied over existing paints and coatings. Many previously coated surfaces may only require one coat. Test DRYLOK® Wet Look on a small area to determine compatibility prior to completing the entire job.

MAINTENANCE INSTRUCTIONS

Horizontal surfaces subject to excessive wear may require periodic touch-ups to high traffic areas.

PRODUCT DATA SHEET

DRYLOK® Wet Look

May 2026, Version 01.02

021820301000000023

DRYLOK®

BUILDING TRUST



LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at www.drylok.com or by calling SIKA’s Technical Service Department at 1-800-272-3235, option 2. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAM-**

AGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/about-us/terms-conditions-of-sale.html> or by calling 1-800-272-3235, option 2.

PRODUCT DATA SHEET

DRYLOK® Wet Look

May 2026, Version 01.02

02182030100000023